This generic SDS is provided by MGS Ltd to give information to assist with material handling of the products listed which are conforming to Regulation (EC) No 1907 / 2006 (REACH)



 Doc No:
 HS8 C42-036

 Version:
 MGS 4/JS

 Date:
 Nov 2023

 Review Date:
 Nov 2024

SECTION 1: Identification of the substance / mixture and of the company / undertaking					
1.1 Product Identifier					
Product Name:	Portland Cement CEM I				
Synonyms / Trade Name:	Cement				
1.2 Relevant identified uses of the substa	ance or mixture and uses advised against				
Recommended Use:	Can be mixed with ballast, sand, and gravel for concreting or together				
	with Bentonite for grouting.				
Restriction on Use:	For industrial purposes only.				
1.3 Details of the supplier of the Safety D	Pata Sheet				
Name:	MGS Ltd				
Address:	Rougham Industrial Estate, Bury St Edmunds, IP30 9ND				
Country:	UK				
Phone N°:	+44 1359 271167				
E-mail:	info@mgs.co.uk				
Website:	www.mgs.co.uk				
1.4 Emergency telephone number					
Emergency telephone at the company	+44 7738 197 517				
Available outside office hours:	Yes				
Language of the phone service:	English				
E-mail of competent person responsible	darren.portway@mgs.co.uk				
National contact:	Darren Portway				

SECTION 2: Hazard Identification

2.1 Classification of the substance or mixture

According to Regulation (EC) No 1272/2008 (CLP)

Hazard Statements

Hazard class	Hazard category	Hazard statements
Skin irritation	2	H315: Causes skin irritation
Serious eye damage/eye irritation	1	H318: Causes serious eye damage
Skin sensitisation	1B	H317: May cause an allergic skin irritation
Specific target organ toxicity single exposure	3	H335: May cause respiratory irritation

2.2 Label elements





Signal word: Danger

This generic SDS is provided by MGS Ltd to give information to assist with material handling of the products listed which are conforming to Regulation (EC) No 1907 / 2006 (REACH)



 Doc No:
 HS8 C42-036

 Version:
 MGS 4/JS

 Date:
 Nov 2023

 Review Date:
 Nov 2024

Precautionary Statement	ts
P102	Keep out of reach of children.
P280	Wear protective gloves/protective clothing/eye protection/face protection.
P305+P351+P338+P310	IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. Immediately call a POISON CENTER or doctor/physician.
P302+P352+P333+P313	IF ON SKIN: Wash with plenty of soap and water. If skin irritation or rash occurs: Get medical advice/attention.
P261+P304+P340+P312	Avoid breathing dust. IF INHALED: Remove victim to fresh air and keep at rest in a position comfortable for breathing. Call a POISON CENTER or doctor/physician if you feel unwell.
P501	Dispose of product/packaging by hardening with the application of water and dispose of as concrete waste.
Other Information	Skin contact with wet cement, fresh concrete or mortar may cause irritation, dermatitis or burns. May cause damage to products made of aluminium or other non-noble metals.
2 3 Other hazards	

2.3 Other hazards

Cement does not meet the criteria for PBT or vPvB in accordance with Annex XIII of REACH (Regulation (EC) No 1907/2006).

When cement reacts with water, for instance when making concrete or mortar, or when the cement becomes damp, a strong alkaline solution is produced. Due to the high alkalinity, wet cement may provoke skin and eye irritation.

The product contains chromate reducing agent. As a result, the content of soluble chromium (VI) is less than 2 ppm. If the storage conditions are not appropriate or the storage period is exceeded, the effectiveness of the reducing agent can diminish, and the cement can become skin sensitizing.

SECTION 3: Composition / Information on Ingredients

3.1 Substances

Not applicable.

This generic SDS is provided by MGS Ltd to give information to assist with material handling of the products listed which are conforming to Regulation (EC) No 1907 / 2006 (REACH)



 Doc No:
 HS8 C42-036

 Version:
 MGS 4/JS

 Date:
 Nov 2023

 Review Date:
 Nov 2024

3.2 Mixtures

Common cement types according to the EN 197-1 standard: CEM I 52,5N CEM I 52,5R CEM I 42,5N CEM II A-LL 32,5R CEM II A-LL 42,5N CEM III A 42,5N LH

which contain less than 1% crystalline silica and:

Substance	Concentration Range	Registration	EINECS	CAS		n Regulation /2008
	(W/W in cement)	Number			Hazard Class	Hazard Statement
					STOT SE 3	H335: May cause respiratory irritation
Portland		(2)	266-	6- 65997	Skin irritation 2	H315: Causes skin irritation
cement 5-100% clinker	(a)	043- 4	- 15-1	Serious eye damage/eye irritation 1 Skin sensitisation 1B	H318: Causes serious eye damage H317: May cause an allergic skin reaction	
		01-	270	60475	STOT SE 3 Skin irritation 2	H335: May cause respiratory irritation H315: Causes
Flue dust (b)	0-5%	211948676 7 -17-0054	270- 659- 9	68475 - 76-3	Serious eye damage/eye irritation 1 Skin sensitisation 1	skin irritation H318: Causes serious eye damage H317: May cause an allergic skin reaction

⁽a) Portland cement clinker is, according to Art. 2.7(b) and Annex V.10 of EC Regulation 1907/2006 (REACH), exempt from the registration requirement.

⁽b) "Flue Dust" is a substance (UVCB), arising during production of cement clinker; other conventional names are cement kiln dust, bypass meal, filter dust, ESP dust and clinker dust.

This generic SDS is provided by MGS Ltd to give information to assist with material handling of the products listed which are conforming to Regulation (EC) No 1907 / 2006 (REACH)



 Doc No:
 HS8 C42-036

 Version:
 MGS 4/JS

 Date:
 Nov 2023

 Review Date:
 Nov 2024

SECTION 4: First Aid Measures 4.1 Description of first aid measures General notes No personal protective equipment is needed for first aid responders. First aid workers should avoid contact with wet cement or wet cement containing mixtures. **Contact with eyes:** Do not rub eyes in order to avoid possible cornea damage as a result of mechanical stress. Remove contact lenses if any. Incline head to injured eye, open the eyelid(s) widely and flush eye(s) immediately by thoroughly rinsing with plenty of clean water for at least 20 minutes to remove all particles. Avoid flushing particles into uninjured eye. If possible, use isotonic water (0.9% NaCl). Contact a specialist of occupational medicine or an eye specialist. Contact with skin: For dry cement, remove and rinse abundantly with water. For wet cement, wash skin with plenty of water. Remove contaminated clothing, footwear, watches, etc. and clean thoroughly before re-using them. Seek medical treatment in all cases of irritation or burns. Move the person to fresh air. Dust in throat and nasal passages should clear spontaneously. **Following** inhalation: Contact a physician if irritation persists or later develops or if discomfort, coughing, or other symptoms persist. Following ingestion: Do not induce vomiting. If the person is conscious, wash out mouth with water and give plenty of water to drink. Get immediate medical attention or contact the anti-poison centre. 4.2 Most important symptoms and effects, both acute and delayed Eye contact with cement (dry or wet) may cause serious and potentially irreversible injuries. Eyes: Skin: Cement may have an irritating effect on moist skin (due to sweat or humidity) after prolonged contact or may cause contact dermatitis after repeated contact. Prolonged skin contact with wet cement or wet concrete may cause serious burns because they develop without pain being felt (for example when kneeling in wet concrete even when wearing trousers). For more details see Reference (1). Inhalation: Repeated inhalation of dust of common cements over a long period of time increases the risk of developing lung diseases. **Environment:** Under normal use, common cement is not hazardous to the environment. 4.3 Indication of any immediate medical attention and special treatment needed When contacting a physician, take this MSDS with you.

This generic SDS is provided by MGS Ltd to give information to assist with material handling of the products listed which are conforming to Regulation (EC) No 1907 / 2006 (REACH)



 Doc No:
 HS8 C42-036

 Version:
 MGS 4/JS

 Date:
 Nov 2023

 Review Date:
 Nov 2024

SECTION 5: Fire Fighting Measures

5.1 Extinguishing media

Cements are not flammable.

5.2 Special hazards arising from the substance or mixture

Cements are non-combustible and non-explosive and will not facilitate or sustain the combustion of other materials.

5.3 Advice for fire fighters

Cement poses no fire-related hazards. No need for special protective equipment for fire fighters.

SECTION 6: Accidental Release Measures

6.1 Personal precautions, protective equipment, and emergency procedures

6.1.1 For non-emergency personnel

Wear protective equipment as described under Section 8 and follow the advice for safe handling and use given under Section 7.

6.1.2 For emergency responders

Emergency procedures are not required. However, respiratory protection is needed in situations with high dust levels. Contact should be avoided with wet cement or wet cement containing mixtures.

6.2 Environmental precautions

Do not wash cement down sewage and drainage systems or into bodies of water (e.g. streams).

6.3 Methods and material for containment and cleaning up

Collect the spillage in a dry state if possible.

Dry cement

Use clean up methods such as vacuum clean-up or vacuum extraction (Industrial portable units, equipped with high efficiency air filters (EPA and HEPA filters, EN 1822-1:2009) or equivalent technique) which do not cause airborne dispersion. Never use compressed air. Alternatively, wipe-up the dust by mopping, wet brushing or by using water sprays or hoses (fine mist to avoid that the dust becomes airborne) and remove slurry. If not possible, remove by slurrying with water (see wet cement). When wet cleaning or vacuum cleaning is not possible and only dry cleaning with brushes can be done, ensure that the workers wear the appropriate personal protective equipment and prevent dust from spreading. Avoid inhalation of cement and contact with skin. Place spilled materials into a container. Solidify before disposal as described under Section 13.

This generic SDS is provided by MGS Ltd to give information to assist with material handling of the products listed which are conforming to Regulation (EC) No 1907 / 2006 (REACH)



 Doc No:
 HS8 C42-036

 Version:
 MGS 4/JS

 Date:
 Nov 2023

 Review Date:
 Nov 2024

Wet cement

Clean up wet cement and place in a container. Allow material to dry and solidify before disposal as described under Section 13.

6.4 Reference to other sections

See Sections 8 and 13 for more details.

SECTION 7: Handling & Storage

7.1 Precautions for safe handling

For more information, refer to the practice guidelines adopted under the Social Dialogue Agreement on Workers' Health Protection through the Good Handling and Use of Crystalline Silica and Products Containing it, by Employee and Employer European sectoral associations, among which CEMBUREAU. These safe handling practices It can be found via the following link:

http://www.nepsi.eu/agreement-good-practice-guide/good-practice-guide.aspx.

7.2 Conditions for safe storage, including any incompatibilities

Bulk cement should be stored in silos that are waterproof, dry (i.e. with internal condensation minimised), clean and protected from contamination. Engulfment hazard: To prevent engulfment or suffocation, do not enter a confined space, such as a silo, bin, bulk truck, or other storage container or vessel that stores or contains cement without taking the proper safety measures. Cement can build-up or adhere to the walls of a confined space. The cement can release, collapse, or fall unexpectedly. Packed products should be stored in unopened bags clear of the ground in cool, dry conditions and protected from excessive draught in order to avoid degradation of quality. Bags should be stacked in a stable manner. Do not use aluminium containers for the storage or transport of wet cement containing mixtures due to incompatibility of the materials.

7.3 Specific end use(s)

No additional information for the specific end uses (see section 1.2).

7.4 Control of soluble Cr (VI)

For cements treated with a Cr (VI) reducing agent according to the regulations given in Section 15, the effectiveness of the reducing agent diminishes with time. Therefore, cement bags and/or delivery documents will contain information on the packaging date, the storage conditions, and the storage period appropriate to maintaining the activity of the reducing agent and to keeping the content of soluble chromium VI below 0.0002 % of the total dry weight of the cement ready for use, according to EN 196-10. They will also indicate the appropriate storage conditions for maintaining the effectiveness of the reducing agent.

This generic SDS is provided by MGS Ltd to give information to assist with material handling of the products listed which are conforming to Regulation (EC) No 1907 / 2006 (REACH)



 Doc No:
 HS8 C42-036

 Version:
 MGS 4/JS

 Date:
 Nov 2023

 Review Date:
 Nov 2024

SECTION 8: Exposure Controls / Personal Protection

8.1 Control parameters

8.1.1 Exposure limit values (Workplace Exposure Limits WEL)

Substance	CAS	Long Term Exposure Limit (8hr TWA Reference Method)	Legal Reference
Portland Cement Clinker		-	
Inhalable dust	65997-15-1	10 mg/m ³	COSHH 2002 & HSE
Respirable dust		4 mg/m ³	EH40/2005

Recommendations given here are based on a DNEL level of 3mg/m3.

8.2 Exposure controls

For each individual PROC, users can choose from either option A) or B) in the table above, according to what is best suited to their specific situation. If one option is chosen, then the same option has to be chosen in the table from section "8.2.2 Individual protection measures such as personal protection equipment" - Specification of respiratory protective equipment. Only combinations between A) – A) and B) – B) are possible.

8.2.1 Appropriate engineering controls

Measures to reduce generation of dust and to avoid dust propagating in the environment such as dedusting, exhaust ventilation and dry clean-up methods which do not cause airborne dispersion.

Exposure Scenario	PROC*	Exposure	Technical Installation	Efficiency
Industrial manufacture /formulation	2, 3		Not required	-
Industrial manufacture/formulation of hydraulic building and construction materials	14, 26		A) Not required or B) Generic local exhaust ventilation	- 78%
	5, 8b, 9	ted shift,	A) General ventilation or B) Generic local exhaust ventilation	17% 78%
Industrial uses of dry hydraulic building and construction materials (indoor, outdoor)	2	stric per ek)	Not required	-
	14, 22, 26	Duration is not restricted (up to 480 minutes per shift, 5 shifts a week)	A) Not required or B) Generic local exhaust ventilation	- 78%
	5, 8b, 9		A) General ventilation or B) Generic local exhaust ventilation	17 % 78 %
Industrial uses of wet suspension of	7	<u> </u>	A) Not required or B) Generic local exhaust ventilation	- 78%
hydraulic building and construction materials	2, 5, 8b, 9, 10, 13, 14		Not required	-

This generic SDS is provided by MGS Ltd to give information to assist with material handling of the products listed which are conforming to Regulation (EC) No 1907 / 2006 (REACH)



 Doc No:
 HS8 C42-036

 Version:
 MGS 4/JS

 Date:
 Nov 2023

 Review Date:
 Nov 2024

Exposure Scenario	PROC*	Exposure	Technical Installation	Efficiency	
	2	not restricted (up to 480 minutes per shift, 5 shifts a week	Not required	-	
Professional use of dry hydraulic building and construction material (indoor, outdoor)	9, 26		A) Not required or B) Generic local exhaust ventilation	- 72 %	
	5, 8a, 8b, 14		o to 480 m week	A) Not required or B) Integrated local exhaust ventilation	- 87 %
	19		Localised controls are not applicable, process only in good ventilated rooms or outdoor	-	
Professional uses of wet suspensions of hydraulic building and construction materials	11		A) Not required or B) Generic local exhaust ventilation	- 72 %	
	2, 5, 8a, 8b, 9, 10, 13, 14, 19	Duration is n	Not required	-	

8.2.2 Individual protection measures such as personal protection equipment General

During work avoid kneeling in fresh mortar or concrete wherever possible. If kneeling is absolutely necessary, then appropriate waterproof personal protective equipment must be worn. Do not eat, drink, or smoke when working with cement to avoid contact with skin or mouth. Before starting to work with cement, apply a barrier cream and reapply it at regular intervals. Immediately after working with cement or cement- containing materials, workers should wash or shower or use skin moisturisers. Remove contaminated clothing, footwear, watches, etc. and clean thoroughly before re-using them.

Eye / Face Protection	Wear approved glasses or safety goggles according to EN 166 when handling dry or wet cement to prevent contact with eyes.	
Skin Protection	Use watertight, wear and alkali resistant gloves (e.g. Nitrile soaked cotton gloves with CE Marking) internally lined with cotton, boots, closed long-sleeved protective clothing as well as skin care products (including barrier creams) to protect the skin from prolonged contact with wet cement. Particular care should be taken to ensure that wet cement does not enter the boots,. For the gloves, respect the maximum wearing time to avoid skin problems. In some circumstances, such as when laying concrete or screed, waterproof trousers or kneepads are necessary.	
Protection Thornal	When a person is potentially exposed to dust levels above exposure limits, use appropriate respiratory protection. The type of respiratory protection should be adapted to the dust level and conform to the relevant EN standard, (e.g. EN 149, EN 140, EN 14387, EN 1827) or national standard.	
Thermal Hazards	Not applicable.	

This generic SDS is provided by MGS Ltd to give information to assist with material handling of the products listed which are conforming to Regulation (EC) No 1907 / 2006 (REACH)



Use	PROC*	Exposure	Specification of respiratory protective equipment (RPE)	RPE efficiency - assigned protection factor (APF)
Industrial	2, 3		Not required	-
manufacture/formulation of hydraulic building and construction materials	14, 26		A) P1 mask (FF, FM) or B) Not required	APF = 4 -
	5, 8b, 9	eek)	A) P2 mask (FF, FM) or B) P1 mask (FF, FM)	APF = 10 APF = 4
	2	× ×	Not required	-
Industrial uses of dry hydraulic building and	14, 22, 26	r shift, 5 shifts a	A) P1 mask (FF, FM) or B) Not required	APF = 4 -
construction materials (indoor, outdoor)	5, 8b,		A) P2 mask (FF, FM) or B) P1 mask (FF, FM)	APF = 10 APF = 4
Industrial uses of wet	7	inutes pe	A) P1 mask (FF, FM) or B) Not required	APF = 4
suspension of hydraulic building and construction materials	2, 5, 8b, 9, 10, 13, 14 Q	Not required	-	
	2	n) pə:	P1 mask (FF, FM)	APF = 4
Professional use of dry hydraulic building and	9, 26 gi	restrict	A) P2 mask (FF, FM) or B) P1 mask (FF, FM)	APF = 10 APF = 4
construction material (indoor, outdoor)	5, 8a, 8b, 14	n is not	A) P3 mask (FF, FM) or B) P1 mask (FF, FM)	APF = 20 APF = 4
	19	Duratio	P2 mask (FF, FM)	APF = 10
	11	ם	A) P2 mask (FF, FM) or B) P1 mask (FF, FM)	APF = 10
Professional uses of wet suspensions of hydraulic building and construction materials	2, 5, 8a, 8b, 9, 10, 13, 14, 19		Not required	APF = 4 -

This generic SDS is provided by MGS Ltd to give information to assist with material handling of the products listed which are conforming to Regulation (EC) No 1907 / 2006 (REACH)



 Doc No:
 HS8 C42-036

 Version:
 MGS 4/JS

 Date:
 Nov 2023

 Review Date:
 Nov 2024

An overview of the APFs of different RPE (according to EN 529:2005) can be found in the glossary of MEASE (16). Any RPE as defined above shall only be worn if the following principles are implemented in parallel: The duration of work (compare with "duration of exposure" above) should reflect the additional physiological stress for the worker due to the breathing resistance and mass of the RPE itself, due to the increased thermal stress by enclosing the head. In addition, it shall be considered that the worker's capability of using tools and of communicating are reduced during the wearing of RPE. For reasons as given above, the worker should therefore be (i) healthy (especially in view of medical problems that may affect the use of RPE), (ii) have suitable facial characteristics reducing leakages between face and mask (in view of scars and facial hair). The recommended devices above which rely on a tight face seal will not provide the required protection unless they fit the contours of the face properly and securely. The employer and self-employed persons have legal responsibilities for the maintenance and issue of respiratory protective devices and the management of their correct use in the workplace. Therefore, they should define and document a suitable policy for a respiratory protective device programme including training of the workers.

8.2.3 Environmental exposure controls

Air

Environmental exposure control for the emission of cement particles into air has to be in accordance with the available technology and regulations for the emission of general dust particles. Storing, loading or unloading cement in bulk prior to further transportation in bulk, blending cement in bulk or using cement in bulk other than at a construction site, including the bagging of cement and cement mixtures, the batching of ready-mixed concrete and the manufacture of concrete blocks and other cement products, requires a permit under the Environmental Permitting Regulations 2010.

Water

Do not wash cement into sewage systems or into bodies of water, to avoid high pH. Above pH 9 negative ecotoxicological impacts are possible.

Soil and terrestrial environment

No special emission control measures are necessary for the exposure to the terrestrial environment.

This generic SDS is provided by MGS Ltd to give information to assist with material handling of the products listed which are conforming to Regulation (EC) No 1907 / 2006 (REACH)



SECTION 9: Physical and	Chemical Properties
· ·	physical and chemical properties
Appearance:	Dry cement is a finely ground solid inorganic material (grey or white powder). Main
	particle size: 5-30 μm.
Odour:	Odourless
Odour threshold:	No odour threshold, odourless.
	/T 20%C in water water called ratio 4:3\; 44.43.5
pH:	(T = 20°C in water, water-solid ratio 1:2): 11-13.5
Melting point:	>1,250°C
Weiting point.	71,230 C
Initial boiling point and	Not applicable as under normal atmospheric conditions, melting point >1,250°C
boiling range:	
Flash point:	Not applicable as is not a liquid.
Evaporation rate:	Not applicable as is not a liquid.
Elammahility (colid	Not applicable as is a solid which is non-combustible and does not cause or contribute to
Flammability (solid gas):	fire through friction.
Upper / Lower	Not applicable as is not a flammable gas.
Flammability or	Not applicable as is flot a flatilitable gas.
explosive limits:	
Vapour pressure:	Not applicable as melting point >1,250°C
.,	, , , , , , , , , , , , , , , , , , ,
Vapour density:	Not applicable as melting point >1,250°C
Relative density:	2.75-3.20; Apparent density: 0.9-1.5 g/cm ³
Cal Lift Park to the	(T. 20%C) -1:-1-1/0.4.4.5/1)
Solubility(ies) in water:	(T = 20°C): slight (0.1-1.5 g/l)
Partition coefficient:	n-octanol/water: Not applicable as is inorganic mixture.
	To octation, water thoughts as is morganic mixture.
Auto-ignition	Not applicable (no pyrophoricity – no organo-metallic, organo-metalloid or organo-
temperature:	phosphine bindings or of their derivatives, and no other pyrophoric constituent in the
•	composition).
Decomposition	Not applicable as no organic peroxide present.
temperature:	
Viscosity:	Not applicable as not a liquid.
Explosive properties:	Not applicable. Not explosive or pyrotechnic. Not in itself capable by chemical reaction of
	producing gas at such temperature and pressure and at such a speed as to cause damage
	to the surroundings. Not capable of a self- sustaining exothermic chemical reaction.
Oxidising properties:	Not applicable as does not cause or contribute to the combustion of other materials.

This generic SDS is provided by MGS Ltd to give information to assist with material handling of the products listed which are conforming to Regulation (EC) No 1907 / 2006 (REACH)



9.2 Other information
Not applicable.
SECTION 10: Stability and Reactivity
10.1 Reactivity
When mixed with water, cements will harden into a stable mass that is not reactive in normal environments.
when mixed with water, terrients will harden into a stable mass that is not reactive in normal environments.
10.2 Chemical stability
Dry cements are stable as long as they are properly stored (see Section 7) and compatible with most other building
materials. They should be kept dry.
Contact with incompatible materials should be avoided. Wet cement is alkaline and incompatible with acids, with
ammonium salts, with aluminium or other non-noble metals. Cement dissolves in hydrofluoric acid to produce
corrosive silicon tetrafluoride gas. Cement reacts with water to form silicates and calcium hydroxide. Silicates in
cement react with powerful oxidizers such as fluorine, boron trifluoride, chlorine trifluoride, managanese trifluoride,
and oxygen difluoride.
10.3 Possibility of hazardous reactions
Cements do not cause hazardous reactions.
10.4 Conditions to avoid
Humid conditions during storage may cause lump formation and loss of product quality.
The state of the s
10.5 Incompatible materials
Acids, ammonium salts, aluminium, or other non-noble metals. Uncontrolled use of aluminium powder in wet
cement should be avoided as hydrogen is produced.
10.6 Hazardous decomposition products
Cements will not decompose into any hazardous products.

This generic SDS is provided by MGS Ltd to give information to assist with material handling of the products listed which are conforming to Regulation (EC) No 1907 / 2006 (REACH)



11.1 Information on toxicological e		F# 4	Deferrer
Hazard class	Cat	Effect	Reference
Acute toxicity - dermal	-	Limit test, rabbit, 24 hours contact, 2,000 mg/kg body weight – no lethality. Based on available data, the classification criteria are not met.	(2)
Acute toxicity- inhalation	-	No acute toxicity by inhalation observed. Based on available data, the classification criteria are not met.	(9)
Acute toxicity - oral	-	No indication of oral toxicity from studies with cement kiln dust.	Literature survey
		Based on available data, the classification criteria are not met.	
Skin corrosion/ irritation	2	Cement in contact with wet skin may cause thickening, cracking or fissuring of the skin. Prolonged contact in combination with abrasion may cause severe burns.	(2) Human experience
Serious eye damage/irritation	1	Portland cement clinker caused a mixed picture of corneal effects and the calculated irritation index was 128. Common cements contain varying quantities of Portland cement clinker, blast furnace slag, gypsum and limestone. Direct contact with cement may cause corneal damage by mechanical stress, immediate or delayed irritation or inflammation. Direct contact by larger amounts of dry cement or splashes of wet cement may cause effects ranging from moderate eye irritation (e.g. conjunctivitis or blepharitis) to chemical burns and blindness.	(10), (11)
Skin sensitisation	1	Some individuals may develop eczema upon exposure to wet cement dust, caused either by the high pH which induces irritant contact dermatitis after prolonged contact, or by an immunological reaction to soluble Cr (VI) which elicits allergic contact dermatitis. The response may appear in a variety of forms ranging from a mild rash to severe dermatitis and is a combination of the two above mentioned mechanisms. If the cement contains a soluble Cr (VI) reducing agent and as long as the mentioned period of effectiveness of the chromate reduction is not exceeded, a sensitising effect is not expected [Reference (3)].	(3), (4)
Respiratory sensitisation	-	There is no indication of sensitisation of the respiratory system. Based on available data, the classification criteria are not met.	(1)

This generic SDS is provided by MGS Ltd to give information to assist with material handling of the products listed which are conforming to Regulation (EC) No 1907 / 2006 (REACH)



 Doc No:
 HS8 C42-036

 Version:
 MGS 4/JS

 Date:
 Nov 2023

 Review Date:
 Nov 2024

Hazard class	Cat	Effect	Reference
Germ cell mutagenicity		No indication. Based on available data, the	(12), (13)
Germ cen mutagementy	_	classification criteria are not met.	
		No causal association has been established	(1)
		between Portland cement exposure and	
		cancer.The epidemiological literature does not	
		support the designation of Portland cement as a	
		suspected human carcinogen.	
		Portland cement is not classifiable as a human	(14)
		carcinogen (According to ACGIH A4: Agents that	(/
		cause concern that they could be carcinogenic for	
		humans but which cannot be assessed	
Carcinogenicity	-	conclusively because of a lack of data. In vitro or	
		animal studies do not provide indications of	
		carcinogenicity that are sufficient to classify the	
		agent with one of the other notations.). Based on	
		available data, the classification criteria are not	
		met.	
		Based on available data, the classification criteria	No evidence
Barrand attacks to		are not met.	from human experience
Reproductive toxicity	-		experience
		Cement dust may irritate the throat and	
		respiratory tract. Coughing, sneezing, and	
		shortness of breath may occur following	(1)
STOT-single exposure		exposures in excess of occupational exposure	. ,
	3	limits. Overall, the pattern of evidence clearly indicates that occupational exposure to cement	
		dust has produced deficits in respiratory function.	
		However, evidence available at the present time is	
		insufficient to establish with any confidence the	
		dose-response relationship for	
		these effects.	
		There is an indication of COPD. The effects are	
STOT-repeated exposure	-	acute and due to high exposures. No chronic	
		effects or effects at low concentration	(15)
		have been observed. Based on available data, the	()
		classification criteria are not met.	
Assistant and a second		Not applicable as cements are not used as an	
Aspiration hazard	-	aerosol.	

Apart from skin sensitisation, Portland cement clinker and common cements have the same toxicological and ecotoxicological properties.

Medical conditions aggravated by exposure

Inhaling cement dust may aggravate existing respiratory system disease(s) and/or medical conditions such as emphysema or asthma and/or existing skin and/or eye conditions.

This generic SDS is provided by MGS Ltd to give information to assist with material handling of the products listed which are conforming to Regulation (EC) No 1907 / 2006 (REACH)



HS8 C42-036 Doc No: Version: MGS 4/JS Date: Nov 2023 Review Date: Nov 2024

12.1 Toxicity

The product is not hazardous to the environment. Ecotoxicological tests with Portland cement on Daphnia magna [Reference (5)] and Selenastrum coli [Reference (6)] have shown little toxicological impact. Therefore LC50 and EC50

values could not be determined [Reference (7)]. There is no indication of sediment phase toxicity [Reference (8)].
The addition of large amounts of cement to water may, however, cause a rise in pH and may, therefore, be toxic to
aquatic life under certain circumstances.
12.2 Persistence and degradability
Not relevant. After hardening, cement presents no toxicity risks.
12.3 Bio accumulative potential
Not relevant. After hardening, cement presents no toxicity risks.
12.4 Mobility in soil
Not relevant. After hardening, cement presents no toxicity risks.
Not relevant. After hardening, cement presents no toxicity risks.
12.5 Results of PBT and vPvB assessment
Not relevant. After hardening, cement presents no toxicity risks.
12.6 Other adverse effects
Not relevant.

This generic SDS is provided by MGS Ltd to give information to assist with material handling of the products listed which are conforming to Regulation (EC) No 1907 / 2006 (REACH)



 Doc No:
 HS8 C42-036

 Version:
 MGS 4/JS

 Date:
 Nov 2023

 Review Date:
 Nov 2024

SECTION 13: Disposal Considerations

13.1 Waste treatment methods

Do not dispose of into sewage systems or surface waters.

Product - cement that has exceeded its shelf life

EWC entry: 10 13 99 (Wastes not otherwise specified)

(and when demonstrated that it contains more than 0.0002% soluble Cr (VI)): shall not be used/sold other than for use in controlled closed and totally automated processes or should be recycled or disposed of according to local legislation or treated again with a reducing agent.

Product - unused residue or dry spillage

EWC entry: 10 13 06 (other particulates and dust)

Pick up dry unused residue or dry spillage as is. Mark the containers. Possibly reuse depending upon shelf life considerations and the requirement to avoid dust exposure. In case of disposal, harden with water and dispose according to "Product – after addition of water, hardened"

Product – slurries

Allow to harden, avoid entry in sewage and drainage systems or into bodies of water (e.g. streams) and dispose of as explained below under "Product - after addition of water, hardened".

Product - after addition of water, hardened

EWC entries: 10 13 14 (waste from manufacturing of cement – waste concrete or concrete sludge) or 17 01 01 (construction and demolition wastes - concrete).

Dispose of according to the local legislation. Avoid entry into the sewage water system. Dispose of the hardened product as concrete waste. Due to the inertisation, concrete waste is not a dangerous waste.

Packaging

EWC entries:15 01 01 (waste paper and cardboard packaging).15 01 02 (Plastic packaging) Completely empty the packaging and process it according to local legislation.

This generic SDS is provided by MGS Ltd to give information to assist with material handling of the products listed which are conforming to Regulation (EC) No 1907 / 2006 (REACH)



SECTION 14: Transportation Information
14.1 UN number
Not relevant
44.2 UN automobilization and au
14.2 UN proper shipping name Not relevant
Not relevant
14.3 Transport hazard class(es)
Not relevant
AA A Deed Comment of the Comment of
14.4 Packing group
Not relevant
14.5 Environmental hazards
Do not discharge into watercourses or drains.
14 C Special processition for user
14.6 Special precaution for user Not relevant
Not relevant
14.7 Transport in bulk according to Annex II of MARPOL 73/78 and the IBC Code
Not relevant

This generic SDS is provided by MGS Ltd to give information to assist with material handling of the products listed which are conforming to Regulation (EC) No 1907 / 2006 (REACH)



 Doc No:
 HS8 C42-036

 Version:
 MGS 4/JS

 Date:
 Nov 2023

 Review Date:
 Nov 2024

SECTION 15: Regulatory Information

15.1 Safety, health, and environmental regulations / legislation specific for the substance or mixture

Cement is a mixture according to REACH and is not subject to registration. Cement clinker is exempt from registration (Art 2.7 (b) and Annex V.10 of REACH).

The marketing and use of cement is subject to a restriction on the content of soluble Cr (VI) (REACH Annex XVII point 47 Chromium VI compounds)

National regulatory information

CONIAC Health Hazard Information Sheet No 26 (CEMENT) Health & Safety at Work, etc. Act 1974
Control of Substances Hazardous to Health Regulations (COSHH) 2002 Control of Substances Hazardous to Health (Amendment) Regulations 2004 Environmental Protection Act 1990
HSE Guidance Note EH40 (Workplace Exposure Limits)

Any authorised manual on First Aid by St.John's/St. Andrews/Red Cross Manual Handling Operations Regulations 1992 (as amended)

PORTLAND CEMENT DUST – criteria document for an occupational exposure limit. June 1994 (ISBN 07176 - 0763 - 1)

HSE Guidance Notes EH26 (Occupational Skin Diseases – Health and Safety Precautions)

15.2 Chemical safety assessment

No chemical safety assessment has been carried out for this mixture by the supplier.

This generic SDS is provided by MGS Ltd to give information to assist with material handling of the products listed which are conforming to Regulation (EC) No 1907 / 2006 (REACH)



 Doc No:
 HS8 C42-036

 Version:
 MGS 4/JS

 Date:
 Nov 2023

 Review Date:
 Nov 2024

SECTION 16: Other Information

16.1 Indication of changes

This MSDS has been reviewed and rewritten to reflect the new structure to meet changes in legislation to the requirements of the CLP regulations (Regulation EC 1272/2008) according to guidelines published by CEMBUREAU, the representative organisation of the cement industry in Europe.

16.2 Identified uses and use descriptors and categories

The table below gives an overview of all relevant identified uses of cement or cement containing hydraulic binders. All the uses have been grouped in these identified uses because of the specific conditions of exposure for human health and environment. For each specific use, a set of risk management measures or localised controls has been derived (see section 8) which need to be put in place by the user of cement or cement containing hydraulic binders to bring the exposure to an acceptable level.

PROC	Identified Uses - Use Description	Manufacture/ Formulation of	Professional/ Industrial use of
11100	identified Oses - Ose Description	building and construction materials	
2	Use in closed, continuous process with occasional controlled exposure, e.g. industrial or professional manufacture of hydraulic binders.	Х	х
3	Use in closed batch process, e.g. industrial or professional manufacture of ready-mix concrete.	X	X
5	Mixing or blending in batch process for formulation of mixtures and articles, e.g. industrial or professional manufacture of precast concrete.	X	X
7	Industrial spraying, e.g. Industrial use of wet suspensions of hydraulic binders by spraying		Х
8a	Transfer of substance or mixture from/to vessels/large containers at non-dedicated facilities, e.g. use of cement in bags to prepare mortar		Х
8b	Transfer of substance or mixture from/to vessels/large containers at dedicated facilities, e.g. filling of silos or road/ rail tankers at cement plants.	Х	Х
9	Transfer of substance or mixture into small containers, e.g. filling of cement bags in cement plants.	Х	Х
10	Roller application or brushing, e.g. Products to improve adherence between building surfaces and finishing products		
11	Non-Industrial spraying, e.g. professional use of wet suspensions of hydraulic binders by spraying.		Х
13	Treatment of articles by dipping and pouring, e.g. covering of construction product with a layer to improve the performance of the product.		Х
14	Production of mixtures or articles by tabletting, compression extrusion, palletisation, e.g. production of floor tiling.	X	Х

This generic SDS is provided by MGS Ltd to give information to assist with material handling of the products listed which are conforming to Regulation (EC) No 1907 / 2006 (REACH)



PROC	Ide	entified Uses - Use Description	Manufacture/ Formulation of	Professional/ Industrial use of	
19	Hand-mixing with intimate contact and only PPE available, e.g. mixture of wet hydraulic binder on a construction site.			х	
22	Potentially closed processing operations with minerals/metals at elevated temperature in Industrial setting, e.g. production of bricks.			х	
26	Handling of solid inorganic substances at ambient temperature, e.g. mixture of wet hydraulic binders.		Х	Х	
16.3 Ab	breviatio	ons and acronyms			
ACGIH		American Conference of Governmental Industrial Hygienists transport of Dangerous goods by Road/Railway	ADR/RID European	Agreements on the	
APF		Assigned protection factor			
CAS		Chemical Abstracts Service			
CLP		Classification, labelling and packaging (Regulation (EC) No 1272/2008) COPD Chronic Obstructive Pulmonary Disease			
DNEL		Derived no-effect level			
EC50		Half maximal effective concentration			
ECHA		European Chemicals Agency			
EINECS		European Inventory of Existing Commercial chemical Substances EPA			
EPA		Type of high efficiency air filter			
ES		Exposure scenario			
EWC		European Waste Catalogue			
FF P		Filtering facepiece against particles (disposable)			
FMP		Filtering mask against particles with filter cartridge			
GefStoff\	/	Gefahstroffverodnung			
НЕРА		Type of high efficiency air filter			
H&S		Health and Safety			
IATA		International Air Transport Association			
IMDG		International agreement on the Maritime transport of Dangerous Goods			
LC50		Median lethal dose			
MEASE		Metals estimation and assessment of substance exposure. EBRC Consulting GmbH for Eurometaux			
MEASE		http://www.ebrc.de/industrial-chemicals-reach/projects-and- references/mease.php			
MS		Member State			

This generic SDS is provided by MGS Ltd to give information to assist with material handling of the products listed which are conforming to Regulation (EC) No 1907 / 2006 (REACH)



MSDS	Material Safety Data Sheet
OELV	Occupational exposure limit value
PBT	Persistent bio-accumulative and toxic
PNEC	Predicted non-effect concentration
PROC	Process category
RE	Repeated exposure
REACH	Registration, Evaluation and Authorisation of Chemicals
RPE	Respiratory protective equipment
SCOEL	Scientific Committee on Occupational Exposure Limit Values
SDS	Safety Data Sheet
SE	Single exposure
STP	Sewage treatment plant
STOT	Specific Target Organ Toxicity
TLV-TWA	Threshold Limit Value-Time-Weighted Average
VLE-MP	Exposure limit value-weighted average in mg by cubic meter of air
vPvB	Very persistent, very bio-accumulative
WEL	Workplace exposure limit
w/w	Weight by weight
WWTP	Waste water treatment plant

This generic SDS is provided by MGS Ltd to give information to assist with material handling of the products listed which are conforming to Regulation (EC) No 1907 / 2006 (REACH)



16.4	Key literature references and sources of data.
1	Portland Cement Dust - Hazard assessment document EH75/7, UK Health and Safety Executive, 2006.
	Available from: http://www. hse.gov.uk/pubns/web/portlandcement.pdf
2	Observations on the effects of skin irritation caused by cement, Kietzman et al, Dermatosen, 47, 5, 184-189 (1999).
3	European Commission's Scientific Committee on Toxicology, Ecotoxicology and the Environment (SCTEE)
	opinion of the risks to health from Cr (VI) in cement (European Commission
	2002).http://ec.europa.eu/health/archive/ph_risk/committees/sct/documents/out158_ en.pdf
4	Epidemiological assessment of the occurrence of allergic dermatitis in workers in the construction industry
	related to the content of Cr (VI) in cement, NIOH, Page 11, 2003.
5	U.S. EPA, Short-term Methods for Estimating the Chronic Toxicity of Effluents and Receiving Waters to
	Freshwater Organisms, 3rd ed. EPA/600/7-91/002, Environmental Monitoring and Support Laboratory, U.S.
	EPA, Cincinnati, OH (1994a) and 4th ed. EPA-821- R-02-013, US EPA, office of water, Washington D.C. (2002).
6	U.S. EPA, Methods for Measuring the Acute Toxicity of Effluents and Receiving Waters to Freshwater and
	Marine Organisms, 4th ed. EPA/600/4-90/027F, Environmental Monitoring and Support Laboratory, U.S. EPA,
	Cincinnati, OH (1993). and 5th ed. EPA-821-R-02-012, US EPA, office of water, Washington D.C. (2002).
7	Environmental Impact of Construction and Repair Materials on Surface and Ground Waters. Summary of
	Methodology, Laboratory Results, and Model Development. NCHRP report 448, National Academy Press,
_	Washington, D.C., 2001.
8	Final report Sediment Phase Toxicity Test Results with Corophium volutator for Portland clinker prepared for
_	Norcem A.S. by AnalyCen Ecotox AS, 2007.
9	TNO report V8801/02, An acute (4-hour) inhalation toxicity study with Portland Cement Clinker CLP/GHS 03-
10	2010-fi ne in rats, July 2010 – unaudited draft approved.
10	TNO report V8815/09, Evaluation of eye irritation potential of cement clinker G in vitro using the isolated
11	chicken eye test, April 2010.
11	TNO report V8815/10, Evaluation of eye irritation potential of cement clinker W in vitro using the isolated
12	chicken eye test, April 2010.
12	Investigation of the cytotoxic and proinflammatory effects of cement dusts in rat alveolar macrophages, Van Berlo et al, Chem. Res. Toxicol., 2009 Sept; 22(9): 1548-58.
13	Cytotoxicity and genotoxicity of cement dusts in A549 human epithelial lung cells in vitro; Gminski et al,
13	Abstract DGPT conference Mainz, 2008.
14	Comments on a recommendation from the American Conference of governmental industrial Hygienists to
14	change the threshold limit value for Portland cement, Patrick A. Hessel and John F. Gamble, EpiLung
	Consulting, June 2008.
15	Prospective monitoring of exposure and lung function among cement workers, Interim report of the study
10	after the data collection of Phase I-II 2006-2010, Hilde Notø, Helge Kjuus, Marit Skogstad and Karl-Christian
	Nordby, National Institute of Occupational Health, Oslo, Norway, March 2010.
16	MEASE, Metals estimation and assessment of substance exposure, EBRC Consulting GmbH for Eurometaux,
10	http://www.ebrc.de/ ebrc/ebrc-mease.php.
17	Occurrence of allergic contact dermatitis caused by chromium in cement. A review of epidemiological
- '	investigations, Kåre Lenvik, Helge Kjuus, NIOH, Oslo, December 2011.

This generic SDS is provided by MGS Ltd to give information to assist with material handling of the products listed which are conforming to Regulation (EC) No 1907 / 2006 (REACH)



 Doc No:
 HS8 C42-036

 Version:
 MGS 4/JS

 Date:
 Nov 2023

 Review Date:
 Nov 2024

16.5 Relevant H Statements

H318: Causes serious eye damage

H315: Causes skin irritation

H317: May cause an allergic skin reaction H335: May cause respiratory irritation

16.6 Training advice

In addition to health, safety and environmental training programs for their workers, companies must ensure that workers read, understand, and apply the requirements of this SDS.

16.7 Further information

The data and test methods used for the purpose of classification of common cements, are given or referred to in section 11.1.

Disclaimer:

This information relates only to the specific material designated and may not be valid for such material used in combination with any other materials or in any process. Such information is, to the best of the company's knowledge and belief, accurate and reliable as of the date indicated. However, no warranty guarantee or representation is made to its accuracy, reliability of completeness. It is the user's responsibility to satisfy themselves as to the suitability of such information for their own particular use.